

LNP™ LUBRILOY™ RX99650 compound

Polyamide 66
SABIC Innovative Plastics

Message:

LNP LUBRILOY* RX99650 is a compound based on Nylon 66 resin containing Proprietary Lubricant. Added feature of this material is: Wear Resistant.
Also known as: LNP* LUBRILOY* Compound PDX-R-99650
Product reorder name: RX99650

General Information			
Additive	Lubricant		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow : 24 hr	2.4 to 2.6	%	
Across Flow : 24 hr	2.4 to 2.6	%	
Water Absorption			
24 hr, 50% RH	0.73	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2220	MPa	ASTM D638
--	2160	MPa	ISO 527-2/1
Tensile Strength			
Yield	60.0	MPa	ASTM D638
Yield	55.0	MPa	ISO 527-2
Break	53.1	MPa	ASTM D638
Break	54.5	MPa	ISO 527-2
Tensile Elongation			
Yield	5.0	%	ASTM D638
Yield	16	%	ISO 527-2
Break	31	%	ASTM D638
Break	64	%	ISO 527-2
Flexural Modulus			
--	2080	MPa	ASTM D790
--	2000	MPa	ISO 178
Flexural Strength			
--	80.7	MPa	ASTM D790

--	74.6	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.31		
vs. Itself - Static	0.18		
Wear Factor - Washer	8.00	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	430	J/m	ASTM D256
23°C ²	19	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	No Break		ASTM D4812
23°C ³	140	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	76.0	J	ASTM D3763
--	65.6	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	207	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	189	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	63.9	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	67.0	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	1.2E-4	cm/cm/°C	
Transverse : -40 to 40°C	1.1E-4	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	282 to 304	°C	
Mold Temperature	93.3 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

