

Toraycon® 5201X10

Polybutylene Terephthalate

Toray Resin Company

Message:

Toraycon® 5201X10 is a Polybutylene Terephthalate (PBT) product. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Impact Resistant

General Information			
UL YellowCard	E41797-233513		
Features	High Impact Resistance		
Part Marking Code	>PBT-I<		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.29	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 3.00 mm ¹	2.5	%	
Flow : 3.00 mm ²	2.0	%	
Water Absorption (23°C, 24 hr)	0.080	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale, 23°C)	70		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2600	MPa	ISO 527-2
Tensile Stress (23°C)	50.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	50	%	ISO 527-2
Flexural Modulus (23°C)	2400	MPa	ISO 178
Flexural Stress (23°C)	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.2	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	290	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	150	°C	ISO 75-2/B
1.8 MPa, Unannealed	55.0	°C	ISO 75-2/A
CLTE - Flow (-30 to 100°C)	1.4E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms · cm	IEC 60093
Electric Strength	19	kV/mm	IEC 60243-1
Dielectric Constant ³			IEC 60250
23°C, 50 Hz	3.40		
23°C, 1 kHz	3.50		

Dissipation Factor ⁴		IEC 60250	
23°C, 50 Hz	2.0E-3		
23°C, 1 MHz	0.020		
Arc Resistance ⁵	130	sec	IEC 60950
Comparative Tracking Index (CTI)	PLC 0	UL 746	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.794 mm)	HB	UL 94	
Additional Information	Nominal Value	Unit	Test Method
Bar Flow Length ⁶ (250°C, 1.00 mm)	8.70	cm	Internal Method
NOTE			
1.	80x80x3		
2.	80x80x3mm		
3.	60% RH		
4.	60% RH		
5.	Tungsten Electrode		
6.	93 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

