

TOPAS® 8007F-04

Cyclic Olefin Copolymer
Topas Advanced Polymers, Inc.

Message:
Film grade

General Information			
Features	Copolymer		
Uses	Films		
Part Marking Code (ISO 11469)	>COC		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
190°C/2.16 kg	2.00	cm ³ /10min	ISO 1133
230°C/2.16 kg	12.0	cm ³ /10min	ISO 1133
Water Absorption (Saturation, 23°C)	0.010	%	ISO 62
Films	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-3
MD	2200	MPa	ISO 527-3
TD	1800	MPa	ISO 527-3
Tensile Stress			ISO 527-3
MD: Fracture	57.0	MPa	ISO 527-3
TD: Fracture	50.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Fracture	2.9	%	ISO 527-3
TD: Fracture	3.0	%	ISO 527-3
Dart Drop Impact ¹	< 36	g	ISO 7765-1
Elmendorf Tear Strength			ISO 6383-2
MD	2.2	N	ISO 6383-2
TD	2.3	N	ISO 6383-2
Oxygen Permeability (23°C, 50% RH)	20	cm ³ ·mm/m ² /atm/24 hr	ASTM D3985
Water Vapor Transmission Rate (38°C, 90% RH)	0.080	g·mm/m ² /atm/24 hr	ISO 15106-3
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ²	78.0	°C	ISO 11357-2
Optical	Nominal Value	Unit	Test Method
Gloss (60°)	> 100		ISO 2813
Haze	< 1.0	%	ISO 14782
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

