

Quadrant EPP TIVAR® 88 BurnGuard

Ultra High Molecular Weight Polyethylene

Quadrant Engineering Plastic Products

Message:

Quadrant EPP TIVAR® 88 BurnGuard is an Ultra High Molecular Weight Polyethylene product. It is available in North America. Typical application: Bags/Liners.
Characteristics include:
Flame Rated
Chemical Resistant
Flame Retardant
High Molecular Weight

General Information			
UL YellowCard	E233006-230133		
Features	Acid Resistant		
	Alcohol Resistant		
	Alkali Resistant		
	Flame Retardant		
	Hydrocarbon Resistant		
	Machinable		
	Solvent Resistant		
	Ultra High Molecular Weight		
Uses	Liners		
Forms	Preformed Parts		
	Profiles		
	Rod		
	Sheet		
	Tubing		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792
Water Absorption			ASTM D570
24 hr	< 0.010	%	
Saturation	< 0.010	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	64		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	641	MPa	ASTM D638
Tensile Strength (Ultimate)	24.8	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	641	MPa	ASTM D790

Flexural Strength (Yield)	19.3	MPa	ASTM D790
Compressive Modulus	448	MPa	ASTM D695
Compressive Strength (10% Strain,23°C)	19.3	MPa	ASTM D695
Coefficient of Friction (vs. Steel - Static)	0.090		Internal Method
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	46.7	°C	ASTM D648
Maximum Use Temperature - Long Term, Air	82	°C	
Limiting Pressure Velocity ¹	0.0701	MPa·m/s	Internal Method
Peak Crystallization Temperature (DSC)	135	°C	ASTM D3418
CLTE - Flow ² (-40 to 149°C)	2.9E-4	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.18 mm, Estimated Rating)	V-0		UL 94
NOTE			
1.	4:1 safety factor		
2.	68°F		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT