

XYRON™ VT31Z

Polyphenylene Ether + PS
Asahi Kasei Chemicals Corporation

Message:

XYRON™ VT31Z is a Polyphenylene Ether + PS (PPE+PS) product filled with 10% filler. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E82268-100063374		
Filler / Reinforcement	Filler,10% Filler by Weight		
Features	Noise Damping		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Molding Shrinkage ¹ (2.00 mm)	0.40 to 0.60	%	Internal Method
Water Absorption (23°C, 24 hr)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	50.0	MPa	ISO 527-2
Nominal Tensile Strain at Break (23°C)	30	%	ISO 527-2
Flexural Modulus (23°C)	2470	MPa	ISO 178
Flexural Stress (23°C)	88.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ² (23°C)	7.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	100	°C	ASTM D648
1.8 MPa, Unannealed	96.0	°C	ISO 75-2/A
CLTE - Flow (-30 to 65°C)	6.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	UL 94		
1.00 mm	V-1		
1.50 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	250 to 290	°C	
Mold Temperature	50.0 to 80.0	°C	

NOTE

- | | |
|----|--------------|
| 1. | 150x150x2 mm |
| 2. | 4 mm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

