

Durethan® C 38 FKAM 000000

Polyamide 6
LANXESS GmbH

Message:
PA 6-Copolymer, non-reinforced, extrusion, medium viscosity, slip agent, nucleated, very supple

General Information				
Additive		Nucleating agent slip agent		
Features		Nucleated smoothness Medium viscosity		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Extrusion		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.13	--	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (235°C/2.16 kg)	5.00	--	cm³/10min	ISO 1133
Water Absorption				ISO 62
Saturated, 23°C	10	--	%	ISO 62
Equilibrium, 23°C, 50% RH	3.0	--	%	ISO 62
Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature ¹	212	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+11	ohms	IEC 60093
Volume Resistivity (23°C)	--	1.0E+13	ohms·cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	--	30	kV/mm	IEC 60243-1
Relative Permittivity (23°C, 1 MHz)	--	3.00		IEC 60250
Additional Information	Dry	Conditioned	Test Method	
ISO Shortname	PA 6/IPDI, ES, 18-020N	--	ISO 1874	
NOTE				

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

