

MAGNUM™ 3325 SLG

ABS Resin

Trinseo

Message:

Super Low Gloss, Medium Heat, Medium Impact ABS resin for injection molded automotive interior trim applications. Magnum 3325 SLG can achieve 60 degree Gardner gloss levels below 2.0 with low gloss gradient across the molded part.

Applications:

Chrysler-MSDB-191A

Ford-WSK-M4D827-A

GM- GMP.ABS.003, GMW15572P-ABS-T2

General Information			
Features	Low Gloss		
	Medium Heat Resistance		
	Medium Impact Resistance		
Uses	Automotive Applications		
	Automotive Interior Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183/B
Apparent Density	0.69	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.1	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.53	%	
Flow	0.52	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2080	MPa	ASTM D638
--	1920	MPa	ISO 527-2
Tensile Strength			
Yield ²	40.0	MPa	ASTM D638
Yield	37.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ³	2.8	%	ASTM D638
Yield	2.8	%	ISO 527-2/50
Break ⁴	22	%	ASTM D638
Break	19	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	2140	MPa	ASTM D790

--	2070	MPa	ISO 178
Flexural Strength			
-- ⁶	64.1	MPa	ASTM D790
--	61.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	11	kJ/m ²	
23°C	16	kJ/m ²	
Notched Izod Impact			
-30°C	130	J/m	ASTM D256
23°C	190	J/m	ASTM D256
-30°C	11	kJ/m ²	ISO 180/A
23°C	18	kJ/m ²	ISO 180/A
Instrumented Dart Impact			ASTM D3763
-30°C, Peak Energy	23.0	J	
23°C, Peak Energy	30.0	J	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	96.7	°C	ASTM D648
0.45 MPa, Unannealed	97.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	82.2	°C	ASTM D648
1.8 MPa, Unannealed	82.0	°C	ISO 75-2/A
Vicat Softening Temperature	101	°C	ISO 306/B50, ASTM D1525 ⁷
CLTE			ASTM E831
Flow : -40 to 100°C	8.3E-5	cm/cm/°C	
Transverse : -40 to 100°C	9.0E-5	cm/cm/°C	
Flammability	Nominal Value	Unit	Test Method
FMVSS Flammability ⁸	24	mm/min	FMVSS 302
Injection	Nominal Value	Unit	
Drying Temperature	82.0 to 85.0	°C	
Drying Time	> 2.0	hr	
Rear Temperature	238	°C	
Middle Temperature	249	°C	
Front Temperature	254	°C	
Nozzle Temperature	249 to 254	°C	
Processing (Melt) Temp	243 to 271	°C	
Mold Temperature	38.0 to 66.0	°C	
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	51 mm/min		

4.	51 mm/min
5.	Method I (3 point load), 1.3 mm/min
6.	Method I (3 point load), 1.3 mm/min
7.	Rate A (50°C/h), Loading 2 (50 N)
8.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

