

OmniCarb™ PC08FR GF20

Polycarbonate

OMNI Plastics, LLC

Message:

20% Glass Reinforced, Flame Resistant Polycarbonate

General Information			
UL YellowCard	E138590-222829		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
UL File Number	E138590		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	93.1	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	5520	MPa	ASTM D790
Flexural Strength	124	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	149	°C	
1.8 MPa, Unannealed, 3.18 mm	146	°C	
Flammability	Nominal Value		Test Method
Flame Rating (3.00 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	249 to 282	°C	
Middle Temperature	260 to 293	°C	
Front Temperature	260 to 293	°C	
Nozzle Temperature	271 to 293	°C	
Processing (Melt) Temp	260 to 293	°C	
Mold Temperature	48.9 to 104	°C	
Back Pressure	0.172 to 0.345	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

