

Verolloy A2606

Acrylonitrile Butadiene Styrene + Nylon

PlastxWorld Inc.

Message:

Verolloy A2606 is an Acrylonitrile Butadiene Styrene + Nylon (ABS+Nylon) product filled with 30% glass fiber. It is available in Europe or North America. Characteristics include:
Flame Rated
High Strength
Impact Resistant

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		High Impact Resistance		
		High Tensile Strength		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Molding Shrinkage - Flow	0.10 to 0.50	--	%	ASTM D955
Water Absorption (24 hr)	0.70	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness	116	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Break)	124	96.5	MPa	ASTM D638
Tensile Elongation (Break)	4.0	6.0	%	ASTM D638
Flexural Modulus	6890	5650	MPa	ASTM D790
Flexural Strength	179	138	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
--	--	190	J/m	
23°C, 3.18 mm	160	--	J/m	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)				
	195	180	°C	ASTM D648
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.50 mm)	HB	--		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

