

# InnoPlus LL7410D

Linear Low Density Polyethylene

PTT Global Chemical Public Company Limited

Message:

InnoPlus LL7410D resin is a linear low density polyethylene with butene comonomers, with high content of slip and antiblock. This grade offers the excellent machinability on conversion lines. Films extruded from InnoPlus LL7410D have high tensile strength, elongation, good toughness and outstanding puncture strength. It is available for tubular blown film processing.

InnoPlus LL7410D is recommended for producing general purpose films, liners, food packaging, heavy duty and agricultural films.

General Information	
Additive	Antiblock
	Slip
Features	Antiblocking
	Butene Comonomer
	Food Contact Acceptable
	Good Toughness
	High Elongation
	High Tensile Strength
	Machinable
	Puncture Resistant
	Slip
Uses	Agricultural Applications
	Film
	Food Packaging
	Liners
Agency Ratings	FDA 21 CFR 177.1520
RoHS Compliance	RoHS Compliant
Forms	Pellets
Processing Method	Blown Film
	Film Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.921	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	52		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method

Tensile Strength			ASTM D638
Yield, Compression Molded	11.0	MPa	
Break, Compression Molded	28.0	MPa	
Tensile Elongation (Break, Compression Molded)	790	%	ASTM D638
Flexural Modulus (Compression Molded)	310	MPa	ASTM D790
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Secant Modulus			ASTM D882
1% Secant, MD : 25 μm, Blown Film	190	MPa	
1% Secant, TD : 25 μm, Blown Film	220	MPa	
Tensile Strength			ASTM D882
MD : Break, 25 μm, Blown Film	34.0	MPa	
TD : Break, 25 μm, Blown Film	26.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 25 μm, Blown Film	700	%	
TD : Break, 25 μm, Blown Film	900	%	
Dart Drop Impact (25 μm, Blown Film)	90	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 25 μm, Blown Film	100	g	
TD : 25 μm, Blown Film	350	g	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	440	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	97.0	°C	ASTM D1525
Peak Melting Temperature	121	°C	ASTM D3418
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 μm, Blown Film)	50		ASTM D2457
Haze (25.0 μm, Blown Film)	17	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	160 to 180	°C	
Die Temperature	170 to 190	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT