

Blendfor® A 6000/V0 NATURALE

Polycarbonate + ABS

SO.F.TER. SPA

Message:

PC/ABS alloy, flame retardant grade, good fluidity and toughness

General Information			
Features	Flame Retardant		
	Good Flow		
	Good Toughness		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage	0.55	%	Internal Method
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	48.0	MPa	ASTM D638
Tensile Elongation (Break)	45	%	ASTM D638
Flexural Modulus	2200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	250	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	115	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Needle Flame Test	Pass		IEC 60695-11-5
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Rear Temperature	180	°C	
Middle Temperature	210	°C	
Front Temperature	220	°C	

Mold Temperature	40.0 to 60.0	°C
------------------	--------------	----

NOTE

- | | |
|----|-----------------------------------|
| 1. | Rate A (50°C/h), Loading 2 (50 N) |
|----|-----------------------------------|

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material
--

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT