Flexalloy® OR 9900-40

Polyvinyl Chloride Elastomer

Teknor Apex Company

Message:

Flexalloy®OR 9900-40 is a polyvinyl chloride elastomer (PVC elastomer) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is: extrusion.

Flexalloy®The main features of OR 9900-40 are:

ROHS certification

high molecular weight

chemical resistance

Typical application areas include:

Hose

Wire and cable

engineering/industrial accessories

Tools

Sealing applications

| General Information | | | |
|--------------------------------------|-----------------------------|-------|-------------|
| Features | Ultra high molecular weight | | |
| | Oil resistance | | |
| Uses | Wire and cable applications | | |
| | Washer | | |
| | Power/other tools | | |
| | Tools/Parts Box | | |
| | Pipe | | |
| | Pipe fittings | | |
| | Seals | | |
| | Footwear | | |
| | rootwear | | |
| RoHS Compliance | RoHS compliance | | |
| Forms | Particle | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.09 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 40 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 6.96 | МРа | ASTM D638 |
| Tensile Elongation (Break) | 300 | % | ASTM D638 |
| Elastomers | Nominal Value | Unit | Test Method |
| Compression Set (70°C, 22 hr) | 32 | % | ASTM D395 |
| Thermal | Nominal Value | Unit | Test Method |
| Continuous Use Temperature | 90.0 | °C | ASTM D794 |

Brittleness Temperature -54.0 °C ASTM D746

Additional Information

膨胀,油浸,ASTM 3号油,125°C,7天:-2.5%动态热稳定性,205°C:>60分钟

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

