ENVIROLOY® ENV15-NC340

Polycarbonate + ABS ENVIROPLAS®, Inc.

Message:

Injection Molding Grade, High Heat Resistance, Excellent Processability, RoHS Compliant NC340 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color. The ENV15 Series Products Are Available With Mold Release and/or UV Stabilizer. Contact Enviroplas Regarding UL Recognized Versions Of This Product.

General Information				
Features	Good Processability			
	High Heat Resistance			
RoHS Compliance	RoHS Compliant			
Appearance	Black			
	Colors Available			
	Natural Color			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.14	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	20	g/10 min	ASTM D1238	
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	53.8	MPa	ASTM D638	
Flexural Modulus	2280	MPa	ASTM D790	
Flexural Strength	86.2	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	590	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, Unannealed	127	°C		
1.8 MPa, Unannealed	106	°C		
Flammability	Nominal Value		Test Method	
Flame Rating (1.50 mm)	НВ		Internal Method	
Injection	Nominal Value	Unit		
Drying Temperature	82.2	°C		
Drying Time	3.0 to 4.0	hr		
Suggested Max Moisture	0.050	%		
Rear Temperature	238 to 260	°C		

Middle Temperature	243 to 271	°C
Front Temperature	249 to 277	°C
Nozzle Temperature	243 to 271	°C
Mold Temperature	76.7 to 98.9	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

