

Starex LX-0957

Acrylonitrile Butadiene Styrene

SAMSUNG SDI CO., LTD.

Message:

Starex LX-0957 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.09	g/cm ³	ASTM D792
--	1.08	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	12	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955, ISO 2577
Flow : 3.20 mm	0.21 to 0.29	%	
Across Flow : 3.20 mm	0.21 to 0.29	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	111		ASTM D785
R-Scale	114		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2200	MPa	ASTM D638
--	2300	MPa	ISO 527-2/5
Tensile Strength			
Yield ²	45.0	MPa	ASTM D638
Yield	49.0	MPa	ISO 527-2/5
Break ³	38.0	MPa	ASTM D638
Break	35.0	MPa	ISO 527-2/5
Tensile Elongation			
Break ⁴	31	%	ASTM D638
Break	20	%	ISO 527-2/5
Flexural Modulus			
-- ⁵	2600	MPa	ASTM D790
-- ⁶	2400	MPa	ISO 178
Flexural Strength			
-- ⁷	69.0	MPa	ASTM D790
-- ⁸	76.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	14	kJ/m ²	ISO 179/1eA

Notched Izod Impact			
23°C, 3.18 mm	170	J/m	ASTM D256
23°C, 6.35 mm	150	J/m	ASTM D256
23°C ¹⁰	14	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 6.40 mm	94.0	°C	ASTM D648
0.45 MPa, Unannealed, 4.00 mm	88.0	°C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	85.0	°C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	77.0	°C	ISO 75-2/A
Vicat Softening Temperature	94.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.20 to 1.32 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
--	2.0 to 4.0	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	160 to 180	°C	
Middle Temperature	190 to 200	°C	
Front Temperature	210 to 220	°C	
Nozzle Temperature	230	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	49.0 to 147	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	5.0 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	2.8 mm/min		
8.	2.0 mm/min		
9.	Thickness: 4 mm		
10.	Thickness: 4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

