

SOLLAMID A 2750 FV

Polyamide 66
Krisoll Resinas Plásticas Ltda.

Message:
SOLLAMID A 2750 FV is a Polyamide 66 (Nylon 66) material filled with glass fiber. It is available in Latin America for injection molding. Primary attribute of SOLLAMID A 2750 FV: Flame Rated.

General Information				
Filler / Reinforcement		Glass Fiber		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.33	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.70 to 0.90	--	%	
Water Absorption (23°C, 24 hr)	0.80	--	%	ASTM D570
Heat Stability	100 to 120	--	°C	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	120	120		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	10000	7500	MPa	ASTM D638
Tensile Strength (23°C)	160	120	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	7.0	%	ASTM D638
Flexural Modulus (23°C)	8500	5500	MPa	ASTM D790
Flexural Strength (23°C)	260	200	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	25	18	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	230	--	°C	
1.8 MPa, Unannealed	230	--	°C	
Melting Temperature	250 to 260	--	°C	
CLTE - Flow	2.5E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	--	ohms · cm	ASTM D257
Dielectric Strength	25	--	kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	HB	--		UL 94
Injection	Dry	Unit		

Processing (Melt) Temp	255 to 260	°C
Mold Temperature	60.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

