

Epiall® 1908B-1

Epoxy; Epoxide

Sumitomo Bakelite North America, Inc.

Message:

Epiall 1908B-1 is a short fiberglass reinforced epoxy molding compound, with excellent dimensional stability, good strength properties and good electrical insulation properties.

General Information			
UL YellowCard	E123472-100085721		
Filler / Reinforcement	Glass Fiber		
Features	Electrically Insulating		
	Good Dimensional Stability		
	Good Strength		
Appearance	Black		
	Blue		
	Green		
Forms	Granules		
Processing Method	Compression Molding		
	Injection Molding		
	Resin Transfer Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.98	g/cm ³	ASTM D792
Apparent Density	0.90	g/cm ³	ASTM D1895
Molding Shrinkage - Flow (Compression Molded)	0.20 to 0.40	%	ASTM D955
Water Absorption - 48 hr (50°C)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	70		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression Molded)	76.0	MPa	ASTM D638
Flexural Modulus (Compression Molded)	15900	MPa	ASTM D790
Flexural Strength (Break)	145	MPa	ASTM D790
Compressive Strength	180	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Annealed, Compression Molded)	> 282	°C	ASTM D648
CLTE - Flow	3.7E-5	cm/cm/°C	ASTM E831
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	12	kV/mm	ASTM D149
Dielectric Constant ¹ (1 MHz)	4.50		ASTM D2520
Dissipation Factor ² (1 MHz)	0.020		ASTM D150
Arc Resistance	180	sec	ASTM D495
Comparative Tracking Index	500	V	IEC 60112, ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating (6.40 mm)	V-0		UL 94
NOTE			
1.	Wet		
2.	Wet		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT