

VITAMIDE® BF30GY6699

Polyamide 6
Jackdaw Polymers

Message:

VITAMIDE® BF30GY6699 is a Polyamide 6 (Nylon 6) product. It is available in Europe. Primary characteristic: flame rated.

General Information			
Appearance	Grey		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792, ISO 1183
Water Absorption			
24 hr	0.90	%	ASTM D570
23°C, 24 hr	0.90	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	65.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	10	%	ASTM D638, ISO 527-2
Flexural Modulus	3050	MPa	ASTM D790, ISO 178
Flexural Strength	75.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	52	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	200	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	80.0	°C	ASTM D648, ISO 75-2/A
Melting Temperature	220	°C	ISO 1218, ASTM D2117
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257, IEC 60093
Dielectric Strength	19	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index			
Solution A	550	V	IEC 60112
-- 1	550	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Oxygen Index	30	%	ASTM D2863, ISO 4589-2
NOTE			

1. Solution A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

