

LG MABS TR530F

Methyl Methacrylate / ABS

LG Chem Ltd.

Message:

Description
Transparency, High Impact, Softness
Application
Artificial nail

General Information			
Features	Impact resistance, high		
	Definition, high		
	Soft		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	88		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	32.4	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	40	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	1470	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	49.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.20 mm	240	J/m	ASTM D256
23°C, 6.40 mm	240	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	74.0	°C	ASTM D648
Optical	Nominal Value	Unit	Test Method
Transmittance	89.0	%	ASTM D1003
Haze	3.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	80 - 90	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	200 - 220	°C	

Middle Temperature	210 - 230	°C
Front Temperature	220 - 240	°C
Nozzle Temperature	220 - 240	°C
Processing (Melt) Temp	220 - 240	°C
Mold Temperature	50 - 70	°C
Back Pressure	29.4 - 58.8	MPa
Screw Speed	< 80	rpm

Injection instructions

Minimum Moisture Content: 0.01%

NOTE

1.	50 mm/min
2.	50 mm/min
3.	15 mm/min
4.	15 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

