

Kostrate® EDGE MT

Thermoplastic

Plastic Selection Group, Inc.

Message:

Kostrate® EDGE MT is a Thermoplastic product. It can be processed by extrusion or extrusion blow molding and is available in North America.

General Information			
Features	Terpolymer		
Processing Method	Extrusion		
	Extrusion Blow Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	31.0	MPa	ASTM D638
Tensile Elongation (Break)	250	%	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Flexural Strength (Yield)	34.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Instrumented Dart Impact (3.18 mm)	5.08	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.18 mm)	79.4	°C	ASTM D648
Optical	Nominal Value	Unit	Test Method
Transmittance	90.0	%	ASTM D1003
Haze	1.5	%	ASTM D1003
Additional Information	Nominal Value	Unit	
Dishwasher Test	3.0E+2	Cycles	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

