

Toughblend® PBT-1200

Polybutylene Terephthalate

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

Message:

Toughblend® PBT-1200 is a glass fiber reinforced compound; offering good mechanical and thermal properties, with additional good chemical resistance.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Chemical Resistance		
Uses	Automotive Applications		
	Industrial Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	87.0	MPa	ASTM D638
Tensile Elongation (Break)	4.5	%	ASTM D638
Flexural Modulus	4100	MPa	ASTM D790
Flexural Strength	135	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	55	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 4.00 mm	215	°C	
1.8 MPa, Unannealed, 4.00 mm	195	°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0 to 6.0	hr	
Rear Temperature	240 to 245	°C	
Middle Temperature	245 to 250	°C	
Front Temperature	255 to 260	°C	
Nozzle Temperature	255 to 260	°C	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	80.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

