

AT 190

Low Density Polyethylene
Celanese EVA Performance Polymers

Message:

This resin is suitable for use in Hot Melt Adhesive, carpet extrusion, and coating applications.

General Information			
Features	Homopolymer		
	High liquidity		
Uses	Sealant		
	Application in Automobile Field		
	Coating application		
	Fiber		
	Adhesive		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Particle		
Processing Method	Extrusion coating		
Physical	Nominal Value	Unit	Test Method
Density	0.914	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (125°C/0.325 kg)	70	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	8.00	MPa	ASTM D638
Tensile Elongation ² (Break)	120	%	ASTM D638
Flexural Modulus - 1% Secant	130	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	102	°C	DSC
Additional Information			
The value listed as Density-Specific Gravity, ASTM D1505, was also tested in accordance with ASTM D1928 ProcC Mod.Ring and Ball Softening Point: 117°C			
NOTE			
1.	Type 4, 50mm/min		
2.	Type 4, 50mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

