

Sumikon® EM-61

Epoxy; Epoxide
SBHPP

Message:

SUMIKON® EM-61 type black is a short fiberglass reinforced epoxy molding compound, with excellent dimensional stability, good strength properties and good electrical insulation properties.

General Information	
Filler / Reinforcement	Glass fiber reinforced material Inorganic filler
Features	Good dimensional stability Insulation Good strength
Appearance	Black
Processing Method	Resin transfer molding Compression molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.89	g/cm ³	JIS K6911
Molding Shrinkage - Flow	0.57	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	9600	MPa	JIS K6911
Flexural Strength	120	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m ²	JIS K6911
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	135	°C	JIS K6911
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	11	kV/mm	JIS K6911

NOTE	
1.	Method B (step by step)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

