

Tarnoform® 500 HI4

Acetal (POM) Copolymer

Grupa Azoty S.A.

Message:

Tarnoform® 500 HI4 there is easy flowing elastomer-modified grade with high impact resistance.

General Information			
Features	Good Flow		
	High Impact Resistance		
Uses	Fasteners		
	Thin-walled Parts		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (2.00 mm)	1.8	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	80.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ISO 527-2/1
Tensile Stress (Yield)	40.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	12	%	
Break	40	%	
Flexural Modulus ¹	1500	MPa	ISO 178
Flexural Stress ²	40.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	170	kJ/m ²	ISO 179/1eU

Notched Izod Impact Strength	11	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	°C	ISO 75-2/A
Vicat Softening Temperature	120	°C	ISO 306/B
Melting Temperature	167	°C	ISO 11357-3
CLTE - Flow (23 to 55°C)	1.2E-4	cm/cm/°C	ISO 11359-2
Limit of Temperature - a few hours operation	100	°C	
Burning Rate	< 100	mm/min	FMVSS 302
ISO Type	POM-K, M-GNPR, 05-001		ISO 1874
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+13	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	20	kV/mm	IEC 60243-1
Dielectric Constant (1 Hz)	4.30		IEC 60250
Dissipation Factor (1 Hz)	0.015		IEC 60250
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	< 0.10	%	
Suggested Max Regrind	10	%	
Processing (Melt) Temp	180 to 210	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	80.0 to 110	MPa	
Injection Rate	Slow-Moderate		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT