

LNP™ THERMOCOMP™ RC004SXC

compound

Polyamide 66

SABIC Innovative Plastics Europe

Message:

LNP THERMOCOMP RC004SXC is a compound based on PA66 resin containing Carbon Fiber. Added features include: Electrically Conductive, Heat Stabilized.

Also known as: LNP* THERMOCOMP* Compound RC004SXC

Product reorder name: RC004SXC

General Information			
Filler / Reinforcement	Carbon Fiber		
Additive	Heat Stabilizer		
Features	Electrically Conductive		
	Heat Stabilized		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.10 to 0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	200	MPa	ISO 527-2/5
Tensile Strain (Break)	3.0	%	ISO 527-2/5
Flexural Modulus ¹	10500	MPa	ISO 178
Flexural Stress	269	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	7.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	35	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	250	°C	ISO 75-2/Af
CLTE - Flow (23 to 60°C)	1.7E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+4	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	

Middle Temperature	282 to 293	°C
Front Temperature	293 to 304	°C
Processing (Melt) Temp	282 to 304	°C
Mold Temperature	93.3 to 110	°C
Back Pressure	0.172 to 0.344	MPa
Screw Speed	30 to 60	rpm

NOTE

1. 2.0 mm/min
2. 80*10*4
3. 80*10*4
4. 80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

