

NOVALAST® 9001

Thermoplastic Vulcanizate

NOVA Polymers, Inc.

Message:

NOVALAST® 9001 is a Thermoplastic Vulcanizate (TPV) material. It is available in North America for blow molding, extrusion, or injection molding. Primary attribute of NOVALAST® 9001: Chemical Resistant.

General Information			
Features	Good Chemical Resistance Good Colorability		
Forms	Pellets		
Processing Method	Blow Molding Extrusion Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.964	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	93		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	13.8	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Tear Strength ¹	43.8	kN/m	ASTM D624
Compression Set			ASTM D395
25°C, 22 hr	33	%	
70°C, 22 hr	47	%	
100°C, 22 hr	57	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-45.6	°C	ASTM D746
Injection	Nominal Value	Unit	Test Method
Processing (Melt) Temp	199	°C	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

