

# Karina IVORY PVC COMPOUND 800-35/ 2-BYR-IS-LMP

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

HEAVY METAL FREE PVC COMPOUND RECOMMENDED FOR JACKETING OF AUTOMOTIVE ELECTRICAL CABLES FOR WORKING AT THE TEMPERATURE RANGE OF - 40C TO 105C.

| General Information                     |                                 |                   |               |
|-----------------------------------------|---------------------------------|-------------------|---------------|
| Uses                                    | Automotive Applications         |                   |               |
|                                         | Cable Jacketing                 |                   |               |
|                                         | Wire & Cable Applications       |                   |               |
| Appearance                              | Ivory                           |                   |               |
| Physical                                | Nominal Value                   | Unit              | Test Method   |
| Density <sup>1</sup>                    | 1.32 to 1.38                    | g/cm <sup>3</sup> | IEC 60811-1-3 |
| Color                                   | OK                              |                   | ME 12         |
| Color a                                 | -1.56 to 1.44                   |                   | ME 12         |
| Color b                                 | 5.18 to 8.18                    |                   | ME 12         |
| Color L                                 | 88.4 to 91.4                    |                   | ME 12         |
| Maximum Variation of Elongation         | < 25                            | %                 | IEC 60811-1-2 |
| Maximum Variation of Tensile Strength   | < 25                            | %                 | IEC 60811-1-2 |
| Hardness                                | Nominal Value                   | Unit              | Test Method   |
| Durometer Hardness (Shore A, 15 sec)    | 78 to 82                        |                   | NBR 7456      |
| Mechanical                              | Nominal Value                   | Unit              | Test Method   |
| Tensile Stress                          | > 14.7                          | MPa               | IEC 60811-1-1 |
| Tensile Strain (Yield)                  | > 200                           | %                 | IEC 60811-1-1 |
| Elastomers                              | Nominal Value                   | Unit              | Test Method   |
| Tensile Strength <sup>2</sup>           | > 14.7                          | MPa               | IEC 60811-1-2 |
| Tensile Elongation <sup>3</sup> (Break) | > 200                           | %                 | IEC 60811-1-2 |
| Electrical                              | Nominal Value                   | Unit              | Test Method   |
| Volume Resistivity <sup>4</sup>         | > 3.0E+13                       | ohms · cm         | NBR 5403      |
| Flammability                            | Nominal Value                   | Unit              | Test Method   |
| Oxygen Index                            | > 26                            | %                 | NBR 6245      |
| NOTE                                    |                                 |                   |               |
| 1.                                      | 24 hr                           |                   |               |
| 2.                                      | Aged in Air for 168 hr at 136°C |                   |               |
| 3.                                      | Aged in Air for 168 hr at 136°C |                   |               |
| 4.                                      | 24 hr                           |                   |               |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

