

# SLOVALEN® PH 99 GB 30 LS

Polypropylene

Plastcom

## Message:

Modified homopolymer PP for injection moulding, chemically reinforced with 30% glass beads, contains the modifier of mechanical properties. Increased strength in comparison with unfilled PP. Applied in all industry branches. Increased strength, toughness, modulus in tension due to the modification. Delivered in natural mode and in the full RAL colour scale.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	UV Stabilizer		
Features	Chemically Coupled		
	General Purpose		
	Good Stiffness		
	Good Strength		
	Good Toughness		
	Homopolymer		
Uses	General Purpose		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PP		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	1.7	%	
Flow	1.6	%	
Water Content	0.050	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3250	MPa	ISO 527-2
Tensile Stress (Yield)	36.0	MPa	ISO 527-2
Tensile Strain (Yield)	8.0	%	ISO 527-2
Flexural Modulus	3100	MPa	ISO 178
Flexural Stress	45.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	4.0	kJ/m²	

23°C	6.0	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
-20°C	34	kJ/m <sup>2</sup>	
23°C	41	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	76.0	°C	ISO 75-2/B
Vicat Softening Temperature	101	°C	ISO 306/B
Melting Temperature (DSC)	160	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	200 to 250	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	70.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

