

Dyflor ME

Polyvinylidene Fluoride

Evonik Industries AG

Message:

Dyflor ME is a Polyvinylidene Fluoride (PVDF) material. It is available in Europe or North America for extrusion, injection molding, or resin transfer molding.

Important attributes of Dyflor ME are:

Flame Retardant

Good UV Resistance

Heat Resistant

General Information			
Features	Flame Retardant		
	Good UV Resistance		
	High Heat Resistance		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
	Resin Transfer Molding		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Specific Heat vs. Temperature (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1780	kg/m ³	ISO 1183 ¹
Melt volume-flow rate (230°C/5.0 kg)	2.00	cm ³ /10min	ISO 1133 ²
Molding Shrinkage			ISO 2577 ³
Flow	2.8	%	
Across Flow	2.2	%	
Water Absorption (Saturation)	0.040	%	ISO 62 ⁴
Mechanical	Nominal Value	Unit	Test Method
Tensile modulus	1690	MPa	ISO 527-2 ⁵
Tensile Stress (Yield)	50.0	MPa	ISO 527-2 ⁶
Tensile Strain (Yield)	9.0	%	ISO 527-2 ⁷
Nominal strain at break	48	%	ISO 527-2 ⁸
Tensile Creep Modulus			ISO 899-1 ⁹
1 hr	1500	MPa	
1000 hr	850	MPa	
Impact	Nominal Value	Unit	Test Method
Charpy notched impact strength			ISO 179/1eA ¹⁰

-30°C	11.0	kJ/m ²	
23°C	32.0	kJ/m ²	
Charpy impact strength			ISO 179/1eU ¹¹
-30°C	260	kJ/m ²	
23°C	310	kJ/m ²	
Tensile notched impact strength (23°C)	210	kJ/m ²	ISO 8256/1 ¹²
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2 ¹³
0.45 MPa	130	°C	
1.8 MPa	70.0	°C	
Vicat Softening Temperature (50°C/h, B (50N))	138	°C	ISO 306 ¹⁴
Melting Temperature ¹⁵	170	°C	ISO 11357-3 ¹⁶
CLTE			ISO 11359-2 ¹⁷
Flow	1.3E-4	cm/cm/°C	
Transverse	1.3E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface resistivity	1.3E+12	ohms	IEC 60093 ¹⁸
Volume resistivity	1.3E+12	ohms · m	IEC 60093 ¹⁹
Electric strength	19	kV/mm	IEC 60243-1 ²⁰
Relative Permittivity			IEC 60250 ²¹
100 Hz	10.6		
1 MHz	6.40		
Dissipation Factor			IEC 60250 ²²
100 Hz	0.026		
1 MHz	0.29		
Comparative tracking index	600		IEC 60112 ²³
Flammability	Nominal Value	Unit	Test Method
Burning Behav. at 1.6mm nom. thickn. (1.50 mm, UL)	V-0		ISO 1210 ²⁴
NOTE			
1.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
2.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
3.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
4.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
5.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		

6.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
7.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
8.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
9.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
10.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
11.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
12.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
13.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
14.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
15.	10 °C/min
16.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
17.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
18.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
19.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
20.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
21.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
22.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
23.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

24.

Tested in accordance with ISO
10350. 23°C/50%r.h. unless
otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

