

Sindustris PC HR5008AE

Polycarbonate
Sincerity Australia Pty Ltd.

Message:

Sindustris PC HR5008AE is a Polycarbonate (PC) material. It is available in Asia Pacific for injection molding.
Important attributes of Sindustris PC HR5008AE are:
Flame Rated
High Flow
Impact Resistant
Typical applications include:
Electrical/Electronic Applications
Housings

General Information			
Features	General Purpose		
	High Flow		
	High Impact Resistance		
Uses	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	5.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	53.9	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	> 100	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2260	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	86.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	45	J/m	
23°C, 3.20 mm	620	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	108	°C	ASTM D648
RTI Elec	60.0	°C	UL 746

RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	240 to 270	°C	
Middle Temperature	245 to 275	°C	
Front Temperature	245 to 275	°C	
Nozzle Temperature	245 to 275	°C	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	50.0 to 70.0	°C	
Screw Speed	40 to 70	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	10 mm/min		
4.	10 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

