

Sumikon® FM-MK209Y

Polyphenylene Sulfide

Sumitomo Bakelite Co., Ltd.

Message:

Engineering plastics molding compounds are developed and marketed materials for metal substitutes, electro-magnetic wave shielding use, and other uses.

General Information			
UL YellowCard	E41429-232853		
Filler / Reinforcement	Carbon fiber reinforced material Organic filler		
Uses	Radiation shielding Metal substitution		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.01	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.20	%	ASTM D955
Transverse flow	0.30	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	102	MPa	ASTM D638
Tensile Elongation (Yield)	0.70	%	ASTM D638
Flexural Modulus	21000	MPa	ASTM D790
Flexural Strength (Yield)	137	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	68	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	260	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+3	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0	hr	

Mold Temperature	120 - 150	°C
------------------	-----------	----

Injection instructions

Cylinder temperature: 290 to 340°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT