

LITEN FB 20

Medium Density Polyethylene

UNIPETROL RPA

Message:

LITEN FB 20 is a medium density copolymer with broad molecular weight distribution and basic stabilization. It can be used for the manufacture of fine packaging films of recommended minimal thickness of 10 µm; it provides soft films even at thicknesses of (30 - 50) µm.

LITEN FB 20 is also suitable for modification of PE-LD film grades, recommended content of FB 20 in PE-LD film being (10 - 30) %. The modified films exhibit improved mechanical properties at lower thickness.

Liten FB 20 meets the hygienic requirements on materials and articles intended for contact with foodstuffs according to Regulation (EC) 1935/2004 of the European Parliament and of the Council, as well as according to Commission Regulation (EU) No 10/2011 including changes and additions.

General Information			
Features	Copolymer		
	Food Contact Acceptable		
	Med.-Wide Molecular Weight Distrib.		
Uses	Film		
	Packaging		
	Plastics Modification		
Agency Ratings	EC 1935/2004		
	EU 10/2011		
Physical	Nominal Value	Unit	Test Method
Density	0.938	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	0.20	g/10 min	
190°C/21.6 kg	20	g/10 min	
190°C/5.0 kg	1.0	g/10 min	
Environmental Stress-Cracking Resistance (50°C, 100% Detergent, F50)	350	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	56		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	17.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	5.0	kJ/m ²	
23°C	14	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT