

Mapex AN0720SB

Polyamide 6

Ginar Technology Co., LTD.

Message:

Mapex AN0720SB is a polyamide 6 (nylon 6) product, which contains a 35% glass fiber reinforced material. It can be processed by injection molding and is available in North America, Africa and the Middle East, Europe or Asia Pacific. Mapex AN0720SB applications include the automotive industry, consumer goods, handles and sporting goods.

Features include:

- Hard
- Heat resistance

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 35% filler by weight		
Features	Rigidity, high		
	Heat resistance, high		
Uses	Handle		
	Application in Automobile Field		
	Sporting goods		
	Toys		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	145	MPa	ASTM D638
Tensile Elongation (Break)	1.9	%	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength	200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	96	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	205	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	

Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Suggested Shot Size	40 - 80	%
Rear Temperature	240 - 250	°C
Middle Temperature	250 - 270	°C
Nozzle Temperature	240 - 250	°C
Mold Temperature	80.0 - 90.0	°C
Back Pressure	0.00 - 0.0981	MPa
Screw Speed	80 - 100	rpm
Injection instructions		

Injection Pressure: 60 to 85% Injection Speed: 60 to 85%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

