

LEXAN™ HFD1930 resin

Polycarbonate

SABIC Innovative Plastics

Message:

55 MFR LEXAN High Flow Ductile Copolymer, Natural color only

General Information			
UL YellowCard	E45329-101013738		
Features	Copolymer		
	High liquidity		
	ductility		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	55	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	51.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2300	MPa	ASTM D638
--	2200	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	60.0	MPa	ASTM D638
Yield	61.0	MPa	ISO 527-2/50
Fracture ³	57.0	MPa	ASTM D638
Fracture	56.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	5.5	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Fracture ⁵	110	%	ASTM D638
Fracture	100	%	ISO 527-2/50

Flexural Modulus			
50.0mm span ⁶	2280	MPa	ASTM D790
-- ⁷	2200	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0mm span ⁸	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	11	kJ/m ²	ISO 179/1eA
23°C	60	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	110	J/m	ASTM D256
0°C	330	J/m	ASTM D256
23°C	670	J/m	ASTM D256
-30°C ¹¹	10	kJ/m ²	ISO 180/1A
23°C ¹²	55	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³			ISO 180/1U
-30°C	No Break		ISO 180/1U
23°C	No Break		ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	56.0	J	ASTM D3763
--	92.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	124	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	110	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁴	120	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	141	°C	ASTM D1525 ¹⁵
--	135	°C	ISO 306/B50
--	136	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	8.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	8.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.582		ASTM D542
Transmittance (2540 µm)	88.0	%	ASTM D1003
Haze (2540 µm)	< 1.0	%	ASTM D1003

Injection	Nominal Value	Unit
Drying Temperature	104 - 110	°C
Drying Time	3.0 - 4.0	hr
Drying Time, Maximum	24	hr
Suggested Shot Size	40 - 60	%
Rear Temperature	238 - 282	°C
Middle Temperature	249 - 293	°C
Front Temperature	260 - 304	°C
Nozzle Temperature	254 - 299	°C
Processing (Melt) Temp	260 - 304	°C
Mold Temperature	48.9 - 82.2	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	35 - 75	rpm
Vent Depth	0.038 - 0.076	mm

NOTE		
1.	5.0 mm/min	
2.	Type 1, 50mm/min	
3.	Type 1, 50mm/min	
4.	Type 1, 50mm/min	
5.	Type 1, 50mm/min	
6.	1.3 mm/min	
7.	2.0 mm/min	
8.	1.3 mm/min	
9.	80*10*3 sp=62mm	
10.	80*10*3 sp=62mm	
11.	80*10*3	
12.	80*10*3	
13.	80*10*3	
14.	80*10*4 mm	
15.	标准 B (120°C/h), 载荷2 (50N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT