

Globalene® SF7351

Polypropylene Alloy

Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® SF7351 is a Polypropylene Alloy (PP Alloy) material. It is available in Asia Pacific or North America for injection molding.

Important attributes of Globalene® SF7351 are:

RoHS Compliant

Good Processability

Impact Resistant

Low Shrinkage

Typical applications include:

Automotive

Engineering/Industrial Parts

Sporting Goods

General Information			
Features	Good Moldability		
	High Impact Resistance		
	Low Shrinkage		
Uses	Automotive Applications		
	Pump Parts		
	Sporting Goods		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.2	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	107		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	80.1	MPa	ASTM D638
Tensile Elongation (Yield)	3.6	%	ASTM D638
Flexural Modulus	5140	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	163	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

