

Verolloy B5526

Acrylonitrile Butadiene Styrene + PBT

PlastxWorld Inc.

Message:

Verolloy B5526 is an Acrylonitrile Butadiene Styrene + PBT (ABS+PBT) product filled with 30% glass fiber. It is available in Europe or North America. Characteristics include:
Flame Rated
Flame Retardant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	118	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	9100	MPa	ASTM D790
Flexural Strength	147	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	155	°C	ASTM D648
RTI Elec	140	°C	UL 746
RTI Imp	95.0	°C	UL 746
RTI Str	130	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	V-0	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT