

LNP™ LUBRICOMP™ DFL32 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP LUBRICOMP DFL32 is a compound based on Polycarbonate resin containing Glass Fiber, PTFE.
Also known as: LNP* LUBRICOMP* Compound DFL-4032
Product reorder name: DFL32

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Additive	PTFE lubricant		
Features	Lubrication		
RoHS Compliance	RoHS compliance		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.20 - 0.40	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4100	MPa	ISO 527-2/1
Tensile Stress (Yield)	74.0	MPa	ISO 527-2/5
Tensile Strain (Yield)	3.2	%	ISO 527-2/5
Flexural Modulus ²	3600	MPa	ISO 178
Flexural Stress	118	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ³ (23°C)	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (-30°C)	35	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵			
0.45 MPa, unannealed, 64.0mm span	146	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 64.0mm span	141	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 60°C	4.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 60°C	8.3E-5	cm/cm/°C	ISO 11359-2
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4		
4.	80*10*4		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT