Moplen RP344R

Polypropylene Random Copolymer

PolyMirae

Message:

Moplen RP344R is a nucleated polypropylene random copolymer manufactured by PMC under the license of BASELL using the Spheripol process. Moplen RP344R is a random copolymer particularly suitable for injection molding of houseware, thin walled articles for food and non food applications, caps and lids

Moplen RP344R meets the FDA requirement in the code of Federal Regulations in 21 CFR 177.1520 for food contact.

General Information						
Additive	Nucleating Agent	Nucleating Agent				
Features	Food Contact Acceptable					
	Good Flow					
	High Gloss					
	Low to No Odor					
	Nucleated					
	Random Copolymer					
Uses	Caps					
	Household Goods					
	Lids					
	Thin-walled Parts					
Agency Ratings	FDA 21 CFR 177.1520					
RoHS Compliance	Contact Manufacturer					
Appearance	Clear/Transparent					
Forms	Pellets					
Processing Method	Injection Molding					
Physical	Nominal Value	Unit	Test Method			
Density	0.900	g/cm³	ASTM D1505			
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	24	g/10 min	ASTM D1238			
Hardness	Nominal Value	Unit	Test Method			
Rockwell Hardness (R-Scale)	90		ASTM D785			
Mechanical	Nominal Value	Unit	Test Method			
Tensile Strength (Yield, Injection Molded)	29.4	MPa	ASTM D638			
Tensile Elongation (Yield, Injection Molded)	8.0	%	ASTM D638			
Flexural Modulus (Injection Molded)	1230	MPa	ASTM D790			
Impact	Nominal Value	Unit	Test Method			
Notched Izod Impact			ASTM D256			
-20°C, Injection Molded	20	J/m				

23°C, Injection Molded	49	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Injection Molded)	95.0	°C	ASTM D648
Optical	Nominal Value	Unit	Test Method
Haze (Injection Molded)	16	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2