

NEOFLON™ EP-620

Ethylene Tetrafluoroethylene Copolymer

DAIKIN AMERICA, INC.

Message:

Resin for heavy wall constructions requiring additional flexibility and lower processing temperatures.

General Information			
Features	Good Flexibility		
Uses	Thick-walled Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.83 to 1.88	g/cm ³	ASTM D3159
Melt Mass-Flow Rate (MFR) (297°C/5.0 kg)	9.0 to 18	g/10 min	ASTM D3159
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.0 to 33.0	MPa	ASTM D3159
Tensile Elongation (Break)	300 to 400	%	ASTM D3159
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	218 to 228	°C	ASTM D3159

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

