

PurSil™ 35 83A

Thermoplastic Polyurethane Elastomer

DSM Biomedical Inc.

Message:

PurSil™ 35 83A is a Thermoplastic Polyurethane Elastomer product. It can be processed by coating, compression molding, dip coating, extrusion, injection molding, or spraying and is available in North America. Applications of PurSil™ 35 83A include medical/healthcare and food contact applications.

Characteristics include:

- Biocompatible
- Good Flexibility
- Hydrolytically Stable

General Information			
Features	Biocompatible		
	Good Flexibility		
	Good Strength		
	Hydrolytically Stable		
	Oxidation Resistant		
Uses	Medical/Healthcare Applications		
Agency Ratings	DMF Unspecified Rating		
	FDA Unspecified Rating		
Appearance	Translucent		
Forms	Pellets		
Processing Method	Coating		
	Compression Molding		
	Dip Coating		
	Extrusion		
	Injection Molding		
	Spraying		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (224°C/1.2 kg)	32	g/10 min	ASTM D1238
Molding Shrinkage - Flow			ASTM D955
-- 1	1.1	%	
-- 2	0.80 to 1.9	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	83		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Ultimate)	25.3	MPa	ASTM D1708
Tensile Stress			ASTM D1708

50% Strain	4.67	MPa	
100% Strain	6.32	MPa	
300% Strain	13.1	MPa	
Tensile Elongation (Break)	490	%	ASTM D1708
Flexural Modulus - 1% Secant	43.3	MPa	ASTM D790
Flexural Strength (5.0% Strain)	1.86	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, H-18 Wheel)	85.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³	57.8	kN/m	ASTM D624
Compression Set (25°C, 22 hr)	29	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-86.0	°C	ASTM D3418
Vicat Softening Temperature	66.7	°C	ASTM D1525
CLTE - Flow	1.9E-4	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	5.80		ASTM D150
Extrusion	Nominal Value	Unit	
Melt Temperature	182 to 204	°C	
NOTE			
1.	4 in disk		
2.	Flame bar		
3.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT