

GAPEX® RPP30EB56BK

Polypropylene Homopolymer

Ferro Corporation

Message:

GAPEX®RPP30EB56BK is a polypropylene homopolymer (PP Homopoly) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

GAPEX®The main features of the RPP30EB56BK are:

Chemical coupling

heat stabilizer

GAPEX®The typical application fields of RPP30EB56BK are: automobile industry

General Information			
Additive	heat stabilizer		
Features	Chemical coupling		
	Thermal Stability		
Appearance	Black		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	0.65	%	ISO 294-4
Flow direction	0.65	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	71.9	MPa	ISO 527-2
Flexural Modulus (23°C)	5000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180
-40°C	4.9	kJ/m ²	ISO 180
23°C	6.8	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	155	°C	ISO 75-2/B
1.8 MPa, not annealed	142	°C	ISO 75-2/A
Additional Information			
Tensile/Izod Change, 1,000 hrs @ 140°C, ISO 188: +7/-12			
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 82.2	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	221 - 238	°C	

Middle Temperature	227 - 243	°C
Front Temperature	232 - 260	°C
Nozzle Temperature	232 - 260	°C
Processing (Melt) Temp	221 - 238	°C
Mold Temperature	37.8 - 65.6	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.138 - 0.345	MPa
Cushion	5.08 - 12.7	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

