

# MIRASON™ 3530

Low Density Polyethylene

Mitsui Chemicals, Inc.

## Message:

MIRASON™ 3530 is a Low Density Polyethylene material. It is available in Asia Pacific.

Important attributes of MIRASON™ 3530 are:

Good Aesthetics

Good Processability

Typical application of MIRASON™ 3530: Electrical/Electronic Applications

General Information			
Features	Good Processability		
	Pleasing Surface Appearance		
Uses	Communication Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.23	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	21.6	MPa	ASTM D638
Tensile Elongation (Break)	650	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-76.0	°C	ASTM D746
Vicat Softening Temperature	98.0	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT