

Kingfa JH960 6111

Polycarbonate + ABS

Kingfa

Message:

Kingfa JH960 6111 is a polycarbonate acrylonitrile butadiene styrene (PC ABS) material. This product is available in North America or Asia Pacific region.

The processing method is injection molding.

The main features of Kingfa JH960 6111 are:

flame retardant/rated flame

Flame Retardant

Strong adhesion

high liquidity

chemical resistance

Typical application areas include:

Electrical/electronic applications

Tools

General Information			
UL YellowCard	E171666-225747		
Features	Good adhesion High liquidity Good chemical resistance Heat resistance, high Hydrolysis resistance Halogen-free Flame retardancy		
Uses	Computer components Electrical/Electronic Applications Power/other tools		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	0.50 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	55.0	MPa	ASTM D638
Tensile Elongation ² (Break)	50	%	ASTM D638
Flexural Modulus ³	2600	MPa	ASTM D790
Flexural Strength ⁴	85.0	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-10°C, 3.20 mm	380	J/m	ASTM D256
23°C, 3.20 mm	500	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	102	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	90.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Dielectric Strength (1.60 mm)	19	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
	V-0		
1.60 mm	5VB		UL 94
	V-0		
3.20 mm	5VA		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	220 - 250	°C	
Middle Temperature	230 - 255	°C	
Front Temperature	235 - 265	°C	
Processing (Melt) Temp	230 - 250	°C	
Mold Temperature	40.0 - 80.0	°C	
Back Pressure	0.300 - 0.700	MPa	
Injection instructions			
Processing Temperature Limit: 270°C Injection Speed: 50 to 80%			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

