

LNP™ STAT-KON™ EE004 compound

Polyether Imide
SABIC Innovative Plastics

Message:

LNP STAT-KON EE004 is a compound based on Polyetherimide resin containing Carbon Fiber. Added features of this material include: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound EC-1004

Product reorder name: EE004

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Features	Conductivity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.10 - 0.30	%	ASTM D955
Transverse flow: 24 hours	0.30 - 0.50	%	ASTM D955
Vertical flow direction: 24 hours	0.30 - 0.50	%	ISO 294-4
Flow direction: 24 hours	0.10 - 0.30	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	14500	MPa	ISO 527-2/1
Tensile Strength			
Fracture	170	MPa	ASTM D638
Fracture	175	MPa	ISO 527-2
Tensile Strain			
Yield	2.0	%	ISO 527-2
Fracture	2.0	%	ASTM D638
Flexural Modulus			
--	12300	MPa	ASTM D790
--	12000	MPa	ISO 178
Flexural Strength			
--	260	MPa	ASTM D790
--	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	59	J/m	ASTM D256
23°C ¹	7.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			

23°C	530	J/m	ASTM D4812
23°C ²	30	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	213	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ³	210	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ISO 11359-2
Flow: -40 to 40°C	1.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 - 1.0E+6	ohms	ASTM D257
Volume Resistivity	1.0E+2 - 1.0E+6	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.500 mm, Testing by SABIC)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121 - 149	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	343 - 354	°C	
Middle Temperature	354 - 366	°C	
Front Temperature	366 - 377	°C	
Processing (Melt) Temp	360 - 366	°C	
Mold Temperature	121 - 149	°C	
Back Pressure	0.344 - 0.689	MPa	
Screw Speed	60 - 100	rpm	
NOTE			
1.	80*10*4		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT