

Accuply® 10

Thermoplastic
Accurate Plastics, Inc.

Message:
A multi use, matte finish, double sided film that will release from most synthetic resin systems: epoxies, phenolic, melamines, rubber, etc. For use in hand layup, from 0 pressure to high pressure applications (1500 PSI) and temperatures to 204 °C (400 °F).
Lamination of thermoset plastics, rubber and most synthetic resins. Highly versatile.

General Information			
Uses	Film		
	Laminates		
	Multilayer Film		
	Sheet		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
	0.0		
Molding Shrinkage - Flow ¹ (190°C)	2.8	%	ASTM D955
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882A
MD : Yield	96.5	MPa	
TD : Yield	96.5	MPa	
MD : Break	172	MPa	
TD : Break	207	MPa	
Tensile Elongation			ASTM D882A
MD : Break	90	%	
TD : Break	60	%	
Thermal	Nominal Value	Unit	
Melting Temperature	260	°C	
NOTE			
1.	Unrestrained 5 minutes		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

