

# Baoding 76-80H

Thermoplastic Polyurethane Elastomer (Polyester)

Baoding Bangtai Polymeric New-Materials Co.,Ltd

Message:

High Water Vapor Transmission  
Processing: Blowing film  
Properties: Excellent stability in machining and outstanding waterproof and breathable.  
Application: Laminated film for clothing, home textiles.

General Information			
Features	Breathable		
	Low to No Water Absorption		
Uses	Consumer Applications		
	Laminates		
	Textile Applications		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	1.18 to 1.22	g/cm <sup>3</sup>	JIS K7311
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	78 to 82		JIS K7311
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			JIS K7311
100% Strain	6.86	MPa	
300% Strain	9.81	MPa	
Tensile Strength	29.4	MPa	JIS K7311
Tensile Elongation (Break)	800	%	JIS K7311
Tear Strength	78	kN/m	JIS K7311
Extrusion	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	3.0 to 5.0	hr	
Melt Temperature	160 to 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

