

Borealis PP RC007

Polypropylene

Borealis AG

Message:

RC007 is a 40% mineral filled polypropylene compound intended for injection moulding.

General Information			
Filler / Reinforcement	Mineral filler, 40% filler by weight		
Features	Rigidity, high		
	Recyclable materials		
	Thermal stability, good		
Uses	Parts under the hood of a car		
	Car interior parts		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.24	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	22	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	35.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	5.0	%	ISO 527-2/50
Flexural Modulus ¹	4800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	2.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	85.0	°C	ISO 75-2/Ae
Vicat Softening Temperature	100	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flammability (1.00 mm)	100	mm/min	ISO 3795
Injection	Nominal Value	Unit	
Mold Temperature	30.0 - 50.0	°C	
Holding Pressure	30.0 - 60.0	MPa	
Injection instructions			
Feeding Temperature: 40 - 80 °C Mass Temperature: 220 - 260 °C Back Pressure: Low to Medium Screw Speed: Low to Medium Flow Front Speed: 100 - 200 mm/s			
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

