

Bergamid™ A70 G15 H NC714

Polyamide 66
PolyOne Corporation

Message:
Glass fiber reinforced PA66 compound with heat stabilized.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	120	MPa	ASTM D638
Flexural Modulus ²	5000	MPa	ASTM D790
Flexural Strength ³	180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	45	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	230	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.6 mm)	HB		Internal method
Injection	Nominal Value	Unit	
Drying Temperature	80 - 90	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	260 - 280	°C	
Middle Temperature	260 - 280	°C	
Front Temperature	260 - 280	°C	
Mold Temperature	65 - 85	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	5.0 mm/min		
2.	1.3 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT