

GLAMIDE® T-401

Polyamide 6

TOYOBO America, Inc.

Message:

GLAMIDE® T-401 is a Polyamide 6 (Nylon 6) product filled with 20% glass fiber. It is available in North America. Primary characteristic: flame rated.

General Information				
UL YellowCard		E51743-242476		
Filler / Reinforcement		Glass Fiber,20% Filler by Weight		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.29	--	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	22	--	g/10 min	ASTM D1238
Molding Shrinkage - Flow				ASTM D955
1.00 mm	0.20 to 0.50	--	%	
3.00 mm	0.50 to 0.80	--	%	
Water Absorption				ASTM D570
24 hr	1.4	--	%	
Equilibrium, 65% RH	2.8	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	118	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength				ASTM D638
Yield, -40°C	150	130	MPa	
Yield, 23°C	125	70.0	MPa	
Yield, 80°C	53.0	38.0	MPa	
Tensile Elongation (Break, 23°C)	3.8	6.0	%	ASTM D638
Flexural Modulus				ASTM D790
-40°C	8000	6600	MPa	
23°C	6300	3200	MPa	
80°C	2900	2400	MPa	
Flexural Strength				ASTM D790
Yield, -40°C	240	115	MPa	
Yield, 23°C	180	100	MPa	
Yield, 80°C	110	58.0	MPa	
Compressive Strength (23°C)	120	--	MPa	ASTM D695
Taber Abrasion Resistance (1000 Cycles, CS-17 Wheel)	10.0	--	mg	ASTM D1044

Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
-40°C	45	60	J/m	
23°C	70	190	J/m	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	217	--	°C	
1.8 MPa, Unannealed	180	--	°C	
CLTE - Flow	3.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	23	17	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	4.00	--		ASTM D150
Dissipation Factor (1 kHz)	0.010	--		ASTM D150
Arc Resistance	100	90.0	sec	ASTM D495
Comparative Tracking Index	550	550	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	HB	--		UL 94
Injection	Dry	Unit		
Processing (Melt) Temp	260 to 280		°C	
Mold Temperature	60.0		°C	
Injection Pressure	30.0 to 55.0		MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT