

PRL PPX-GP8

Polyphenylene Ether + PS

Polymer Resources Ltd.

Message:

PRL PPX-GP8 is a Polyphenylene Ether + PS (PPE+PS) product. It can be processed by injection molding and is available in North America.

Characteristics include:

RoHS Compliant

Heat Resistant

Impact Modified

Impact Resistant

General Information			
Additive	Impact Modifier		
Features	General Purpose		
	High Impact Resistance		
	Impact Modified		
	Medium Heat Resistance		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/11.6 kg)	14 to 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	44.8	MPa	
Break, 3.18 mm	44.8	MPa	
Tensile Elongation (Break, 3.18 mm)	50	%	ASTM D638
Flexural Modulus (3.18 mm)	1970	MPa	ASTM D790
Flexural Strength (Break, 3.18 mm)	68.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C, 3.18 mm	190	J/m	
23°C, 3.18 mm	370	J/m	
Gardner Impact (3.18 mm)	16.9	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	116	°C	
1.8 MPa, Unannealed, 3.18 mm	110	°C	

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257

Injection	Nominal Value	Unit
Drying Temperature	104 to 110	°C
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	243 to 293	°C
Middle Temperature	254 to 299	°C
Front Temperature	266 to 304	°C
Processing (Melt) Temp	274 to 302	°C
Mold Temperature	65.6 to 98.9	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

