

STABAMID® 25 RS 5

Polyamide 66
Solvay Polyamide & Intermediates

Message:
Semi-dull

General Information		
Uses	Textile Applications	
Forms	Pellets	
Physical	Nominal Value	Unit
Density	1.14	g/cm ³
Apparent Density	0.70	g/cm ³
Humidity - at Packaging	< 0.40	%
Relative Viscosity		
Formic Acid 90%	41.0	
Sulfuric Acid 96%	2.51	
Viscosity		
Formic Acid 90%	122	cm ³ /g
Sulfuric Acid 96%	135	cm ³ /g
Amino End Groups	49	meq/kg
Carboxyl End Groups	80.0	meq/kg
Granulometry ¹	3.00	
Thermal	Nominal Value	Unit
Melting Temperature ²	257	°C
Peak Crystallization Temperature (DSC)	214	°C
NOTE		
1.	g/100 chips	
2.	2nd melting	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT